

ENTROPY OF ALUMINUM AT LOW TEMPERATURES

Link to: [physicspages home page](#).

To leave a comment or report an error, please use the auxiliary blog.

Reference: Daniel V. Schroeder, *An Introduction to Thermal Physics*, (Addison-Wesley, 2000) - Problem 3.14.

A curve fit to experimental measurements of the heat capacity of one mole of alumin(i)um at low temperatures is

$$C_V = aT + bT^3 \quad (1)$$

where $a = 0.00135 \text{ J K}^{-2}$ and $b = 2.48 \times 10^{-5} \text{ J K}^{-3}$.

We can use this to work out the entropy from the formula

$$S_f - S(0) = \int_0^{T_f} \frac{C_V(T)}{T} dT \quad (2)$$

$$= aT_f + \frac{b}{3}T_f^3 \quad (3)$$

If we take $S(0) = 0$, we can evaluate the formula at a few temperatures.

At $T = 1 \text{ K}$, we have

$$S(1) = 1.358 \times 10^{-3} \text{ J K}^{-1} \quad (4)$$

In dimensionless form, we have

$$\frac{S(1)}{k} = 9.84 \times 10^{19} \quad (5)$$

At $T = 10 \text{ K}$

$$S(10) = 0.0218 \text{ J K}^{-1} \quad (6)$$

$$\frac{S(10)}{k} = 1.58 \times 10^{21} \quad (7)$$